

TEST CERTIFICATE ON FLAMMABILITY TESTING OF UPHOLSTERY COMPOSITE

No. 5/BP/21

Test method:

PN-EN 1021-1:2014-12 Furniture. Assessment of the ignitability of upholstered furniture. Part 1: Ignition source smouldering cigarette.

Orderer*:

Subject of testing*:

Upholstery composite:

- upholstery fabric named MIU, composition: 100% Polyester,
- T-3037 polyurethane foam, self-extinguish

Testing sample with the correct size, in appropriate state for testing,
supplied by the Orderer with its characteristic and without the Sampling Protocol.




Sieć Badawcza Łukasiewicz-
Instytut Włókiennictwa
LABORATORIUM BADAŃ
PALNOŚCI WYROBÓW
90-520 Łódź, Gdańska 118
tel. 42 25 34 435, fax 42 25 34 490

Results of testing:

Standard	Test method	Result
PN-EN 1021-1:2014-12	Ignition source: smouldering cigarette	Neither progressive smouldering ignition nor flaming ignition occurred.

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Tests performed by:


Krzysztof Kostanek Ph.D.

Test Certificate authorized by


mgr inż. Małgorzata Szejna

Sample received on: 07.01.2021
Test performed on: 29.01.2021
Test Certificate issued on: 29.01.2021

NOTES:

1. The Testing results refer only to the tested sample.
2. Test Certificate consists of 2 pages.
3. Test Certificate must not be reproduced in another way, than as a whole without a prior written consent of the Testing Laboratory.
4. The Orderer using this Test Certificate is responsible for the conformity between the product and sample submitted for testing.
5. *Data provided by the Customer.

The Testing Laboratory accredited by the Polish Centre for Accreditation (PCA), No AB 029.

DETAILED TESTING RESULTS

Climate conditions: temperature $(23 \pm 2) ^\circ\text{C}$; humidity $(50 \pm 5) \%$; time 24 h
 Testing conditions: temperature 22°C ; humidity 30 %

Preparation of test samples:

the upholstery fabric, exposed to wetting in water and drying procedure, in accordance with Appendix D of the PN-EN 1021-1:2014-12 standard.

Upholstery composite characteristic:

Upholstery composite:

- upholstery fabric named MIU, composition: 100% Polyester,
- T-3037polyurethane foam, self-extinguish.

Criteria		Cigarette			Remarks
		1	2	3	
Smouldering criteria	Unsafe escalating combustion	NO	NO	-	Maximum cigarette smouldering time: 13 minutes 11 seconds
	Test assembly consumed	NO	NO	-	
	Smoulders to extremities	NO	NO	-	
	Smoulders through thickness	NO	NO	-	Maximum upholstery composite destruction:
	Smoulders more than 1 hour	NO	NO	-	
	In final examination, presence of active smouldering	NO	NO	-	
Flaming criteria	Occurrence of flames	NO	NO	-	horizontal [mm]
					vertical [mm]
					length width depth length width depth
					72 14 9 66 14 5

Result of testing: Neither progressive smouldering ignition nor flaming ignition occurred.

END OF THE TEST CERTIFICATE